



nome prodotto : CERIO OSSIDO SUPERPOL

www.andreagallo.it

MEC-POL FO500S

Cerium Oxide

FIELDS OF APPLICATION

- Pre-silver cleaning of mirrors
- Glass and mirror bevelling

PHYSICAL AND CHEMICAL DATA

Average Particle size (Coulter Counter) d50:
pH-value of slurry:
Loss on ignition:

TYPICAL

1,7 – 2,3 μm
6,0 – 7,0
2,4 %

INSTRUCTIONS FOR USE:

Concentration of slurry:	Pre-silver cleaning:	20 – 30 g/l
	Bevelling:	50 – 60 g/l
Suggested slurry temperature:	35 – 40 °C	
Polishing pads:	Whatever is suitable and brushes	

PACKING:

PE-containers with 25 kgs net each

CAUTIONS:

Use normal Industrial precautions

07/02/07