



distribuito da:
ANDREA GALLO DI LUIGI S. r. l.
azienda fondata nel 1892
Via Erzelli, 9 - 16152 Genova (Italy)
Tel. 010.650.29.41
www.andreagallo.it

Technical Data Sheet

GRASSO SILICONICO 55 CALSIL PER O-RING

Brand CALSIL
Market Machinery & Equipment
Product name GRASSO SILICONICO 55 CALSIL PER O-RING

1. Product Description

GRASSO SILICONICO 55 CALSIL PER O-RING consists of Silicone oil with lithium soap.

2. Key Properties

- Compatible to extreme temperatures (from - 70°C up to + 180°C).
- NLGI consistency : N.2
- Low variation of the consistency in temperature

3. Benefits

- Résistance to heat: Slight lowering of viscosity with increasing temperature but does not decompose and gives a long service life.
- Very little change in consistency with temperature: does not stiffen when cold, does not thin out at high temperatures.
- Very good stability, especially in contact with water and most corrosive media.

4. Applications

- Dynamic lubrication in aeronautical pneumatic systems.
- Lubrication of toroidal joints and seals in the car industry.
- Lubrication of rings on metallic shafts.

Typical Properties (not for sales specifications, please contact us prior to writing sales specs)

Properties	Units	Values
Chemical composition		Silicone oil and Lithium Soap
Appearance		Filamentous fluid grease
Color		Light Brown
Worked penetration at 25°C ASTM D 217 – 68		265-295
NLGI consistency		N.2
Specific gravity at 25°C approx		0.98-1.00
Freezing point	°C	-65
Boiling point	°C	ND
Flash point	°C	>240
Drop point	°C	200
Service range	°C	-65+175

5. How to Use

It is recommended to be applied on clean and dry surfaces (degreased if necessary).

GRASSO SILICONICO 55 CALSIL PER O-RING could be applied with a brush, with a paint brush, with a spatula or with a paste gun.

6. Remarks

- GRASSO SILICONICO 55 CALSIL PER O-RING should not be applied to surfaces which are to be painted.
- GRASSO SILICONICO 55 CALSIL PER O-RING is not recommended for the lubrication of taps and valves for oxygen systems. This is because silicones in contact with oxygen under pressure may cause explosions.

7.

Silicone Oils and Phenyl Trimethicone	Compatible
Aliphatic Solvents	Soluble
Aromatic Solvents	Soluble
Water	Insoluble
Mineral Greases	Not compatible
EPDM-EPM-NBR-SBR-NR-IR-BR-IIR	Compatible
MFQ-MPQ-MPVQ-MQ-MVQ	Not compatible
Gas	Not compatible
Liquid gas	Not compatible
Contact with drinking water	None
Incidental food contact	None
Water washout resistance	None
Resistance to fuels (oil, gasoline, Diesel oil, ...)	None
Resistance to polar liquid	Yes
Resistance to no polar liquid	None



8. Handling

This document does not contain safety precautions. Before handling this material, please read the Material Safety Data Sheet, check the label on the container, and conform to the safety, physical and hazard guidelines and precautions.

9. Storage and Shelf Life

This product should be stored in its original unopened containers at a temperature between +2 °C and + 40°C. It can be used within the 18 months following its production date.

10. Packaging

Available in:

- 100 Gr. tubes
- 5 Kg pails on request

11. Restrictions

This ingredient is solely proposed in the above listed applications.

It is not suitable to be used in medical, human injection, pharmaceutical or food applications.

12. Limited Warranty PLEASE READ CAREFULLY

- The information herein is offered in good faith. It is believed to be accurate at the time of shipment.
- It should not be used as a substitute for the customer's test, the customer bears the responsibility to ensure that the product matches the intended application is safe and achieves the desired benefits.
- The product warranty is limited to the refund value of the purchase or the replacement only when it is demonstrated that the product is out of the agreed sales specifications.