

LOCTITE STYCAST G 508-1

September 2015

PRODUCT DESCRIPTION

LOCTITE STYCAST G 508-1 provides the following product characteristics:

Technology	Epoxy
Appearance	Black
Product Benefits	<ul style="list-style-type: none"> • One component • Flame retardant • High temperature resistance • Heat, water and chemical resistant • Low coefficient of thermal expansion • High thermal conductivity
Operating Temperature	-40 to +180°C
Cure	Heat cure
Application	Encapsulation

LOCTITE STYCAST G 508-1 pourable, one component, flame retardant encapsulant is recommended for use high temperature applications.

LOCTITE STYCAST G 508-1 is UL certified VO, Class H. File Number: E70278 (M).

TYPICAL PROPERTIES OF UNCURED MATERIAL

Density, g/cm ³	1.58
Viscosity, Brookfield, 25 °C, mPa·s (cP)	27,000
Storage Life @ 25°C, days	180
Pot Life :	
@ 45°C, ± 50% viscosity reduction, days	1 to 2
@ 60°C, ± 90% viscosity reduction, hours	3 to 4

TYPICAL CURING PERFORMANCE

Gel Time

- 1 hour @ 120°C
- 8 minutes @ 160°C
- 4 minutes @ 180°C

Cure Schedule

- 2 hours @ 120°C
- 30 minutes @ 160°C
- 12 minutes @ 180°C

Recommended cure schedule for minimum shrinkage during cure is 3 hours @ 120°C.

This product may generate excessive heat if cured in thicknesses greater than 10 mm at a temperature above 125°C. Dielectric strength and other evaluated temperature and electrical properties can be further improved by post-curing for 1 hour @ 180°C or 2 hours @ 150°C.

The above cure profile is a guideline recommendation. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Hardness, Shore D:	
@ 25°C (minimum)	85
@ 120°C	70
Thermal Conductivity, W/(m-K)	0.7
Glass Transition Temperature, °C:	
by TMA	118
by DMA	133
Coefficient of Linear Thermal Expansion:	
Below Tg, ppm/°C	36
Above Tg, ppm/°C	118
Young's modulus (E) :	
@ -40°C	N/mm ² 5,152 (psi) (747,234)
@ -20°C	N/mm ² 4,945 (psi) (717,211)
@ 0°C	N/mm ² 4,737 (psi) (687,043)
@ 25°C	N/mm ² 4,537 (psi) (689,944)
@ 50°C	N/mm ² 4,309 (psi) (624,967)
@ 100°C	N/mm ² 3,642 (psi) (528,227)
@ 150°C	N/mm ² 75 (psi) (10,877)
@ 200°C	N/mm ² 86 (psi) (12,473)

Electrical Properties

Volume Resistivityohm-cm:	
@ 25°C	1×10 ¹⁴
@ 180°C	1×10 ¹⁰

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE

1. For best results when potting small electrical components, preheat device (and mold, if used) above °C before pouring the epoxy to remove moisture from the device. If lower viscosity is desired, this product may be preheated to temperatures up to 60 °C.
2. This product contains oxide filler specially selected to give high thermal conductivity and low coefficient of expansion. This filler may cause abrasion of valves or nozzles of some dispensing equipment.



STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : 25 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{psi} \times 145 = \text{N/mm}^2$
 $\text{MPa} = \text{N/mm}^2$
 $\text{N} \cdot \text{m} \times 8.851 = \text{lb} \cdot \text{in}$
 $\text{N} \cdot \text{m} \times 0.738 = \text{lb} \cdot \text{ft}$
 $\text{N} \cdot \text{mm} \times 0.142 = \text{oz} \cdot \text{in}$
 $\text{mPa} \cdot \text{s} = \text{cP}$

Disclaimer

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 1