



distribuito da:
ANDREA GALLO DI LUIGI S. r. l.
azienda fondata nel 1892
Via Erzelli, 9 - 16152 Genova (Italy)
Tel. 010.650.29.41
www.andreagallo.it

Technical data sheet

PARAFFINA TECNICA RP56

ANALYSIS	METHOD	UNIT	RANGE
Congealing point	ASTM D938	°C	58-67
Colour	ASTM D1500		1,5-4,5
Oil content	ASTM D721	%	6-14
Cone penetration at 25°C	ASTM D937	dmm	25-35
Specific gravity at 15°C	ASTM D1298	Kg/l	0,830-0,855
Flash point	ASTM D93	°C	>200
Viscosity at 100°C	ASTM D445	cst	5-7

Data stampa: 01 Luglio 2016