



distribuito da:  
**ANDREA GALLO DI LUIGI S. r. l.**  
azienda fondata nel 1892  
Via Erzelli, 9 - 16152 Genova (Italy)  
Tel. 010.650.29.41  
[www.andreagallo.it](http://www.andreagallo.it)

Data Sheet

Grade  
BC 200

# ARBOCEL

Natural cellulose fibers

## Basic raw material

Highly pure cellulose

## Characteristics

Medium sized fiber, white

## Chemical and physical properties

Cellulose content	~	99.5 %
Oxide ash (850 °C, 4 h)	~	0.3 %
Whiteness (absolute value at 460 nm)		81 % - 91 %
pH-value (10 % suspension)		5 - 7
Average fiber length		300 µm
Average fiber thickness		20 µm
Bulk density (in accordance with DIN EN ISO 60)		70 g/l - 90 g/l

**Screen analysis** (in accordance with DIN EN ISO 4610/air jet sieve) with an interior mesh aperture of:

<u>&gt; 300 µm</u>	<u>&gt; 100 µm</u>	<u>&gt; 32 µm</u>
max. 0.5 %	max. 15 %	40 % - 80 %

## General remarks

ARBOCEL cellulose fibers are environment friendly products, gained from replenishable raw materials. Among other things, they are used as thickeners, for fiber reinforcement, as an absorbent and diluent or as a carrier and filler in most manifold application fields.

As with all natural products slight differences to the above given values may arise.

Cellulose CAS-Nr.: 9004-34-6

Release date: 2013-08 / 1 page



**J. RETTENMAIER & SÖHNE GMBH + CO KG**  
Fibers designed by Nature  
Holzmühle 1  
D-73494 Rosenberg

Telephone: +49 7967 152-0  
Telefax: +49 7967 152-222