



ANDREA GALLO DI LUIGI S.r.l.

[azienda fondata nel 1892](#)

Via Erzelli, 9 - 16152 Genova (Italy)

Tel. 010.650.29.41 - Fax 010.650.38.88

www.andreagallo.it

Data Sheet

POLPA DI CELLULOSA

ARBOCEL BE 600-10 TG

Natural cellulose fibers

Basic raw material

Highly pure cellulose

Characteristics

Short fiber, white

Chemical and physical properties

Cellulose content	~	99.5 %
Oxide ash (850 °C, 4 h)	~	0.3 %
Whiteness (absolute value at 460 nm)		80 % - 90 %
pH-value (10 % suspension)		5 - 7
Average fiber length		18 µm
Average fiber thickness		15 µm
Bulk density (in accordance with DIN EN ISO 60)		230 g/l - 300 g/l

Screen analysis (in accordance with DIN EN ISO 4610/air jet sieve) with an interior mesh aperture of:

> 50 µm	> 32 µm
traces	max. 0.5 %

General remarks

ARBOCEL cellulose fibers are environment friendly products, gained from replenishable raw materials. Among other things, they are used as thickeners, for fiber reinforcement, as an absorbent and diluent or as a carrier and filler in most manifold application fields.

As with all natural products slight differences to the above given values may arise.

Cellulose CAS-Nr.: 9004-34-6